



Acoustic / Thermal Polyester Insulation

Premium quality - Adelaide made

Product Overview

Description

Premium quality **Adelaide** made polyester batts for high performance acoustic and thermal insulation needs in residential, social venue, commercial and industrial soundproofing applications.

Quality Assured

Air Diffusion Batts are made to the highest standards and comply with the building code of Australia AS/NZS4859.1

Ratings and sizes

R-Value (m2K/W)	Batt Size	Batts/pack M2		Density kg	NRC
R2.0	1170 x 580 x 90	8	5.42	20	0.95
R2.0	1170 x 430 x 90	8	4.02		
R2.5	1170 x 580 x 90	6	4.07	28	1.00
R2.5	1170 x 430 x 90	6	3.02		
R2.5/32	1170 x 580 x 90	5	3.39	32	1.07

Fire Resistance

When tested in Accordance to AS1530 Part 3. Air Diffusion Agencies products meet these requirements.

Ignitability Index 0	Range 1-20
Spread of Flame Index 0	Range 1-10
Heat Evolved Index 0	Range 1-10
Smoke developed Index 0-1	Range 1-10

Applications

- Behind perforated panels, ceilings and acoustic systems to reduce the echo in halls, cinemas, plantroom and HVAC equipment.
- Cavity infill to reduce low frequency noise transfer through partitions, walls, home theatre rooms, entertainment areas and floors.
- Reduce flanking noise through ceiling cavities and suspended ceilings.



ABN 32 768 939 131

Acoustic / Thermal Polyester Insulation



Premium quality – Adelaide made

Physical Description

Properties: non-allergenic, low irritant, low flame response and resilient

Environmental: Very good environmentally as much of the raw materials used in the manufacture is recycled material P.E.T packaging such as plastic bottles. No ozone depleting or harmful materials used in the manufacture.

Melting Point: 250c

Maximum Service Temp: 150c

Flammability: Non-flammable and complies with the building code of Australia

Moisture Absorption: Exposed to an atmosphere of 50c, 90% RH for four days gives moisture absorption of less than 0.03% by volume

Ingredients: Organic, Long Chain Synthetic Polymer

Chemical Entity: Composed of Carbon-Hydrogen Oxygen

Alkalinity: pH 7.8 (pH 7 is neutral)

Corrosiveness: The product is not classified as corrosive

Percentage Volatilizes: No harmful (VOC) volatile organic components



ABN 32 768 939 131

Peter 0468 356 600

info@thesilencer.com.au

www.thesilencer.com.au